





UN38.3 TEST REPORT UN38.3 检测报告

Report No.:

报告编号:

CMC241014041

Name of Goods:

物品名称:

Lithium-ion Rechargeable Battery

锂离子可充电电池

Model:

型号:

702530 3.7V 500mAh

Type:

规格:

3.7V 500mAh 1.85Wh

Client:

委托单位:

HUAYOU NEW ENERGY (DONGGUAN) CO., LTD

华友新能源(东莞)有限公司

Classification

of test: 检测类别: **Commission Test**

委托测试

Tested by:

主检人:

Ri Ley Xiao 有差

Approved by:

批准人:

Inspected by:

审核人:

Dylan Dou 室 明記

Date of Issue:

签发日期:

2024.10.31

Seal of CMC: CMC 印章: To Control of Control

CMC Testing International (Shenzhen) Co., Ltd.

众检检验认证 (深圳) 有限公司

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 1 / 18



TEST REPORT 检测报告

	1	<u> </u>	7777						
Name of Goods 物品名称	Lithium-ion Battery 锂离子可充	Rechargeable 电电池	Model 型号	702530 3.7	530 3.7V 500mAh				
Commissioner 委托单位		UAYOU NEW ENERGY (DONGGUAN) CO., LTD 全友新能源(东莞)有限公司							
Commissioner's Address 委托单位地址	Huangjiang	F, Building A, Changxing Zhigu Industrial Park, No.16, Xinfeng Street, Changlong Village, langjiang Town, Dongguan City 莞市黄江镇长龙村新风街 16 号常兴智谷产业园 A 栋 6 楼							
Manufacturer 制造商		EW ENERGY (DONG (东莞) 有限公司	GUAN) CO., LTD						
Manufacturer's Address 制造商地址	Huangjiang	6 / F, Building A, Changxing Zhigu Industrial Park, No.16, Xinfeng Street, Changlong Village Huangjiang Town, Dongguan City 东莞市黄江镇长龙村新风街 16 号常兴智谷产业园 A 栋 6 楼							
Manufacturer's Contact Telephone 制造商联系电话	+86-	15915430383	E-mail 邮箱 Web 网址	rd@hyhy-	battery.com				
Trade Mark/ identification 商标/识别码		Shape 形状	Cuboid 长方体	Size 尺寸 (LxWxT)	(32.5×24.8×6.8)m m				
Nominal Voltage 标称电压	3.7V	Charge Voltage 充电电压	4.2V	Rated Capacity 额定容量	500mAh				
Cell Model 电池型号	702530	Cell Nominal Voltage 电池标称电压	3.7V	Cell Rated Capacity 电池额定容量	500mAh				
Cells Number 电池数量	1PC	Sample Receiving Date 样品接收日期	2024.10.14	Testing Date 测试日期	2024.10.14 — 2024.10.29				
Test conclusion 检测结论	ST/SG/AC.	The sample has passed the test items of UNITED NATIONS "Manual of Tests and Criteria" ST/SG/AC.10/11/Rev.7/ Amend.1 Subsection 38.3 经测试,该样品符合联合国《试验和标准手册》(第 7 修订版 修正 1)38.3 标准要求。							

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 2 / 18



Test Standard 检测标准

UN "Manual of Tests and Criteria" ST/SG/AC.10/11/Rev.7/Amend.1 Subsection 38.3

联合国《试验和标准手册》 (第7修订版 修正1) 38.3 节

Description and illustration of the sample: The sample's status is good.

样品说明及描述:样品状况良好。

Test item 检测项目	Sample No. 样品编号	State 状态	Remark 备注		
T 14 T 15	B001~B005	B001~B005 At first cycle, in fully charged states 第 1 个充电周期,完全充电状态			
Test 1 ~ Test 5	B006~B010	After 25 cycles ending in fully charged states 第 25 个充电周期,完全 <mark>充</mark> 电 <mark>状态</mark>			
T-+0	C001~C005	At first cycle at 50% of the design rated capacity 第1个充放电周期 50%设计额定容量状态			
Test 6	C006~C010	After 25 cycle at 50% of the design rated capacity 第25个充放电周期 50%设计额定容量状态			
	B011~B014	At first cycle, in fully charged states 第 1 个充电周期,完全充电状态			
Test 7	B015~B018	After 25 cycles ending in fully charged states 第 25 个充电周期,完全充电状态			
T 10	C011~C020	At first cycle in fully discharged states 第1个充放电周期,完全放电状态			
Test 8	C021~C030	After 25 cycles ending in fully discharged states 第25个充放电周期,完全放电状态			

CXXX is used as the sample number of cells SN241014041CXXX, "X" is 0~9.

CXXX 代表电芯样板编号 SN241014041CXXX, X=0~9。

BXXX is used as the sample number of batteries SN241014041BXXX, "X" is 0~9

BXXX 代表电池包样板编号 SN241014041BXXX, X=0~9。

Description of the deviation from the standard, if any:

检测结果不符合标准项的说明:

Test environment conditions: Ambient temperature: 25° C $\pm 5^{\circ}$ C, Ambient humidity: 45%-75%

检测环境条件: 环境温度: 25℃±5℃; 环境湿度: 45%-75%

Remarks:

备注:

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 3 / 18



ST/SG/AC.10/11/Rev.7/Amend.1 Subsection 38.3						
Clause 章节	Requirements 标准要求	Result 测试结果	Verdict 判定			
38.3.4	Procedure 检测步骤					
38.3.4.1	Test 1: Altitude simulation 检测 1: 高度模拟					
	Test cells and batteries shall be stored at a pressure of 11.6kPa or less for at least six hours at ambient temperature (20±5°C). 将电池和电池组在温度为 20±5°C,大气压力为不大于 11.6kPa 的环境中贮存不少于 6 小时。					
	Requirements 标准要求: 1) Cells and batteries Mass loss limit reference: Table 38.3.1 样品质量损失限值参考:表 38.3.1 2) Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后开路电压应不低于试验前开路电压的 90%,此要求不适用于完全放完电的电池或电池组。 3) No leakage, no venting, no disassembly, no rupture and no fire. 样品(电池)应无渗漏、无排气、无解体、无破裂以及无起火现象的发生。	The samples B001~B010: No leakage, no venting, no disassembly, no rupture and no fire. 编号为 B001~B010 的样品: 无渗漏、无排气、无解体、无破裂以及无起火现象。 The data is shown in Test T.1 数据见表 T.1	Pass 合格			

38.3.4.2 Test 2: Thermal test 检测 2: 温度试验

Test cells and batteries are to be stored for

电池和电池组存储条件如下:

1) For small cells and batteries: one temperature cycle: 72±2°C (6h) ~ -40±2°C (6h)

对于小型电池和电池组: 一次温度循环为 72±2°C (6h)~-40±2°C (6h)

For large cells and batteries: one temperature cycle: 72±2°C (12h) ~ -40±2°C (12h)

对于大型电池和电池组: 一次温度循环为 72±2°C (12h) ~ -40±2°C (12h)

2) The maximum time interval between test temperature extremes is 30minutes. 温度转换最大间隔时间为 30min。

3) This procedure is to be repeated 10 times. 重复 10 次循环。

4) after which all test cells and batteries are to be stored for 24 hours at ambient temperature (20±5°C). 循环结<mark>束后,电池和电池</mark>组在 20±5°C 的条件下搁置 24 小时。

Requirement 标准要求:

- 1) Cells and batte<mark>ries Mass loss li</mark>mit reference: Table 38.3.1 样品质量损失限值参考:表 38.3.1
- 2) Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states.

样品试验后开路电压应不低于试验前开路电压的 90%,此要求不适用于完全放完电的电池和电池组。

3) No leakage, no venting, no disassembly, no rupture and no fire. 样品(电池)应无渗漏、无排气、无解体、无破裂以及无起火现象的发生。

The samples B001~B010: No leakage, no venting, no disassembly, no rupture and no fire. 编号为 B001~B010 的样品: 无渗漏、无排气、无解体、无破裂以及无起火现象。

The data is shown in Table T.2 数据见表 T.2

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 4 / 18

Pass 合格



		Report No.: CMC2410	014041		
Clause 章节	ST/SG/AC.10/11/Rev.7/Amend.1 Subse Requirements 标准要求	ection 38.3 Result 测试结果	Verdict 判定		
	Test 3: Vibration 检测 3: 振动 1) Cells and batteries are firmly secured to the platform of the vibration machine. 电池和电池组牢固地安装在振动台(的台面)上。 2) The vibration: a sinusoidal waveform with a logarithmic sweep between 7Hz and 200Hz and back to 7Hz traversed in 15 minutes. 振动以正弦波形式,以 7Hz 增加至 200Hz,然后在减少回到 7Hz 为一个循环,一个循环持续 15 分钟的对数前移传送。 3) For cells and small batteries: from 7Hz a peak acceleration of 1gn is maintained until 18Hz is reached. The amplitude is then maintained at 0.8mm (1.6mm total excursion) and the frequency increased until a peak acceleration of 8gn occurs (approximately 50Hz). A peak acceleration of 8gn is then maintained until the frequency is increased to 200Hz. 对于电池和小型电池: 从 7Hz 开始,以 1gn 的峰值加速度保持不变,直到达到 18Hz。然后将振幅保持在 0.8mm(总偏移 1.6mm)并且频率增加直到出现 8gn 的峰值加速度(大约 50Hz)。然后保持 8gn 的峰值加速度,直到频率增加到 200Hz。				
	For large batteries: from 7Hz a peak acceleration of 1gn is main The amplitude is then maintained at 0.8mm (1.6mm total excurs increased until a peak acceleration of 2gn occurs (approximate of 2gn is then maintained until the frequency is increased to 20 对于大型电池: 从 7Hz 开始,以 1gn 的峰值加速度保持不变,持在 0.8mm(总偏移 1.6mm)并且频率增加直到出现 2gn 的峰保持 2gn 的峰值加速度,直到频率增加到 200Hz。 4) This cycle repeated 12 times for a total of 3 hours for each comounting position of the cell. One of the directions of vibration terminal face.	rsion) and the frequency ely 25Hz). A peak acceleration 10Hz. 直到达到 18Hz。然后将振幅保 值加速度(大约 25Hz)。然后 of three mutually perpendicular must be perpendicular to the	Pass 合格		
	以振动的其中一个方向必须是垂直样品极性,对每个电池从三年个方向 3 个小时,共 9 小时。 Requirements 标准要求: 1) Cells and batteries Mass loss limit reference: Table 38.3.1 样品质量损失限值参考:表 38.3.1 2) Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后开路电压应不低于试验前开路电压的 90%,此要求不适用于完全放完电的电池和电池组。 3) No leakage, no venting, no disassembly, no rupture and no fire. 样品(电池)应无渗漏、无排气、无解体、无破裂以及无起火现象的发生。	The samples B001~B010: No leakage, no venting, no disassembly, no rupture and no fire. 编号为 B001~B010 的样品: 无渗漏、无排气、无解体、无破裂以及无起火现象。 The data is shown in Table T.3 数据见表 T.3			

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 5 / 18



ST/SG/AC.10/11/Rev.7/Amend.1 Subsection 38.3							
Clause 章节	Requirements 标准要求	Result 测试结果	Verdict 判定				
38.3.4.4	Test 4: Shock 检测 4: 冲击						
	1) Test cells and batteries shall be secured to the testing machine. 以稳固的托架固定住每个电池和电池组样品的全部配件表面。 2) Each cell shall be subjected to a half-sine shock of peak acceleration of 150gn and pulse duration of 6 milliseconds. Large cells may be subjected to a half-sine shock of peak acceleration of 50gn and pulse duration of 11 milliseconds. 对每个电池以峰值为 150gn 的半正弦的加速度撞击,脉冲持续 6ms,大型电池须经受最大加速度 50gn 和脉冲持续时间 11ms 的半正弦波冲击。 Small batteries shall be subjected to a half-sine shock of peak acceleration of 150gn (or						
	Acceleration $(g_n) = \sqrt{\frac{100850}{mass}}$, which is smaller) aneration of $50g_n$ (or Acceleration(g_n)= $\sqrt{\frac{30000}{mass}}$,					
	which is smaller) and pulse dud pulse duration of 6 milliseconds, large batteries shall be						
	subjected to a half-sine of peak accelration of 11 milliseconds.						
	的加速度撞击,脉冲持续 6ms,						
	大型电池须经受最大加速度 50gn(或与√(³⁰⁰⁰⁰)中的较小值)和B	k冲持续时间 11ms 的半正弦波	Pass				
	冲击。 3) Each cell or battery shall be subjected to three shocks in the positive direction followed by three shocks in the negative direction of three mutually perpendicular mounting positions of the cell or battery for a total of 18 shocks. 每个电池或电池组须在三个互相垂直的电池安装方位的正方向经受三次冲击,接着在反方向经受三次冲击,总共经受 18 次冲击。						
	Requirements 标准要求: 1) Cells and batteries Mass loss limit: ≤0.2%. 样品质量损失≤0.2% 2) Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后开路电压应不低于试验前开路电压的 90%,此要求不适用于完全放完电的电池或电池组。 3) No leakage, no venting, no disassembly, no rupture and no fire. 样品(电池)应无渗漏、无排气、无解体、无破裂以及无起火现象的发生。	The samples B001~B010: No leakage, no venting, no disassembly, no rupture and no fire. 编号为 B001~B010 的样品: 无渗漏、无排气、无解体、无破裂以及无起火现象。 The data is shown in Table T.4 数据见表 T.4					

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 6 / 18



Clause 章节	Requirements 标准要求	Result 测试结果	Verdict 判定		
38.3.4.5	Test 5: External Short Circuit 检测 5: 外部短路				
	1) The cell or battery to be tested shall be heated for a period of time necessary to reach a homogeneous stabilized temperature 57±4°C. 加热电池或电池组样品直到温度稳定在 57±4°C 2) The cell or battery shall be subjected to a short circuit condition with a total external resistance of less than 0.1 ohm at 57±4°C, This short circuit condition is continued for at least one hour after the cell or battery external case temperature has returned to 57±4°C. 将样品正负极用小于 0.1Ω 的总电阻回路进行短路,样品的外表温度恢复到 57±4°C 之后保持短路状态 1 小时以上。 3) The cell or battery must be observed for a further six hours for the test to be concluded. 对电池或电池组必须进一步观察 6 个小时才能下结论。				
	Requirements 标准要求: 1) Cells external temperature not exceed 170°C. 电池的最高表面温度应不超过 170°C。 2) No disassembly, no rupture and no fire during the test and within six hours after the test. 测试中与测试后 6 小时内无解体、无破裂、无起火。	The samples B001~B010: No leakage, no venting, no disassembly, no rupture and no fire. 编号为 B001~B010 的样品: 无解体、无破裂以及无起火现象。 The data is shown in Table T.5 数据见表 T.5			

38.3.4.6	Test 6: Impact / <mark>Crush</mark> 检测 6: 撞击/挤压	Pass 合格
	Impact (applicable to cylindrical cells not less than 18mm in diameter) 撞击(适用于直径不小于 18 毫米的圆柱形电池)	
	1) This test sample cell or component cell is to be placed on a flat smooth surface. 将试验样品用的电池或元件电池放在一个平坦光滑的平面上 2) A 15.8 mm diameter bar is to be placed across the center of the sample, A 9.1kg mass is to be dropped from a height of 61±2.5cm onto the sample. 将一直径为 15.8mm 的不锈钢圆棒横过电池中部放置后,将一质量为 9.1kg 的物体从 61±2.5cm 的高度落向样品。 3) The test sample is to be impacted with its longitudinal axis parallel to the flat surface and perpendicular to the longitudinal axis of the 15.8mm ± 0.1mm diameter curved surface lying across the center of the test sample. Each sample is to be subjected to only a single impact. 接受撞击的试样,纵轴应与平坦的表面平行并与横放在试样中心的直径 15.8±0.1 毫米弯曲表面的纵轴垂直。每一个试样只经受一次撞击。	N/A 不适用
	Requirements 标准要求: 1) Cells external temperature not exceed 170°C. 电池的最高表面温度应不超过 170°C。 2) No disassembly, no rupture and no fire during the test and within six hours after the test. 测试中与测试后 6 小时内无解体、无破裂、无起火。	

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 7 / 18



	ST/SG/AC.10/11/Rev.7/Amend.1 Subse	ction 38.3	
Clause 章节	Requirements 标准要求	Result 测试结果	Verdict 判定
	Crush (applicable to prismatic, pouch, coin/button cells and cylin diameter). 挤压(适用于棱柱形、袋装、硬币/纽扣电池和直径小于 18 毫米		
	1) A cell or component cell is to be crushed between two flat su gradual with a speed of approximately 1.5cm/s at the first point be continued until the first of the three options below is reached 将电池或元件电池放在两个平面之间挤压,挤压力度逐渐加大,为 1.5 厘米/秒。挤压持续进行,直到出现以下三种情况之一: (a) The applied force reaches 13kN ± 0.78kN. 施加的力达到 13 千牛顿±0.78 千牛顿。 (b) The voltage of the cell drops by at least 100mV. 电池的电压下降至少 100 毫伏。 (c) The cell is deformed by 50% or more of its original thickness 电池变形达原始厚度的 50%或以上。 2). A prismatic or pouch cell shall be crushed by applying the force on its flat the crush force shall be applied perpendicular to the longitudin 棱柱形或袋装电池应从最宽的一面施压。纽扣/硬币形电池应从其从与纵轴垂直的方向施压。	t of contact. The crushing is to d. 在第一个接触点上的速度大约 s. proce to the widest side. A t surfaces. For cylindrical cells, all axis.	Pass 合格
	1) Cells external temperature not exceed 170°C. 电池的最高表面温度应不超过 170°C。 2) No disassembly, no rupture and no fire during the test and within six hours after the test.	No leakage, no venting, no disassembly, no rupture and no fire. 编号为 C001~C010 的样品: 无解体、无破裂、无	
	测试中与测试后 6 小时内无解体、无破裂、无起火。	起火现象。 The data is shown in Table T.6 数据见表 T.6	

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 8 / 18



ampere).

Requirements 标准要求:

days after the test.

Report No.: CMC241014041

	ST/SG/AC.10/11/Rev.7/Amend.1 Subsection 38.3	011102 1110	
Clause 章节	Requirements 标准要求 Result		Verdict 判定
38.3.4.7	Test 7: Overcharge 检测 7: 过度充电		
	1) The charge current shall be twice the manufacturer's recommended maximum corcharge current. 以制造商建议的最大持续充电电流的两倍对样品充电。 2) The minimum voltage of the test shall be as follows: 试验的最小电压如下: a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage battery or 22V. 制造商建议的充电电压不大于 18V 时,试验的最小电压应是电池组最大充电电压的两位两者中的较小者。 b) when the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. 制造商建议的充电电压大于 18V 时,试验的最小电压应为最大充电电压的 1.2 倍。3) Tests are to be conducted at ambient temperature 20±5°C, The duration of the test 24 hours. 试验应在环境温度(20±5°C)下进行。进行试验的时间应为 24 小时。	tage of 音或 22V mum	Pass 合格
	Requirements 标准要求: No disassembly and no fire during the test and within seven days after the test. 试验过程中和试验后 7 天内无解体,无起火。 The samples B011~I No disassembly and 编号为 B011~B018 自无解体、无起火现象 The data is shown in T.7 数据见表 T.7	no fire. 的样品 : 。	
38.3.4.8	Test 8: Forced d <mark>ischarge</mark> 检测 8: 强制放电		
	Each cell shall be forced discharged at ambient temperature by connecting it in serie 12V D.C. power supply at an initial current equal to the maximum discharge current supply the manufacturer. 每个电池应在环境温度(20±5°C)下与 12V 直流电源串联在起始电流等于制造商给定放电电流的条件下强制放电。	specified	
	The specified discharge current is to be obtained by connecting a resistive load of the appropriate size and rating in series with the test cell. Each cell shall be forced discharatime interval (in hours) equal to its rated capacity divided by the initial test current (in hours).	arged for	Pass 合格

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

将适当大小和额定<mark>值的电阻负荷与</mark>试验电池串联,计算得出给定的放电电流。对每个电池进行

The samples C011~C030:

no disassembly and no fire. 编号为 C011~C030 的样品:

无解体、无起火现象。 The data is shown in Table

T.8 数据见表 T.8

强制放电,放电时间(小时)应等于其额定容量除以初始试验电流(安培)。

No disassembly and no fire during the test and within seven

试验过程中和试验后7天内无解体,无起火。

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 9 / 18



ST/SG/AC.10/11/Rev.7/Amend.1 Subsection 38.3

General terms and definitions 一般术语与定义

Table 38.3.1:Mass loss limit 表 38.3.1:质量损失限值

Mass M of cell or battery 电池或电池组质量 M	Mass loss limit 质量损失限值
M < 1 g	0.5%
1 g ≤ M ≤75 g	0.2%
M > 75 g	0.1%

In order to quantify the mass loss, the following procedure is provided:

Mass loss (%) = $(M_1 - M_2)/M_1 \times 100$

质量损失的量化值,可用以下公式计算:

质量损失(%) = $(M_1 - M_2)/M_1 \times 100$

Where M1 is the mass before the test and M2 is the mass after the test. When mass loss does not exceed the values in Table 38.3.1, it shall be considered as "no mass loss".

式中: M1 是试验前的质量, M2 是试验后的质量。如果质量损失不超过表 38.3.1 所列的数值, 应视为"无质量损失"。

Leakage means the visible escape of electrolyte or other material from a cell or battery or the loss of material (except battery casing, handling devices or labels) from a cell or battery such that the loss of mass exceeds the values in Table 38.3.1.

渗漏是指可以看到的电解<mark>液或者其他物质从电池或电池组中漏出,或电池或电</mark>池组中的物质损失(不包括电池外壳、搬运装置、或标签),质量损失超过表 **38.3.1** 所列的数值。

Venting means the release of excessive internal pressure from a cell or battery in a manner intended by design to preclude rupture or disassembly.

排气是指按设计方式释放电池或电池组内部过高的压力,防止其破裂或解体。

Disassembly means a vent or rupture where solid matter from any part of a cell or battery penetrates a wire mesh screen (annealed aluminium wire with a diameter of 0.25 mm and grid density of 6 to 7 wires per cm) placed 25 cm away from the cell or battery.

解体是指排气或破裂使电<mark>池或电池组任何</mark>部分的<mark>固体物质穿过放</mark>在离电池或电池 **25** cm 处的丝网筛(直径 **0.25** mm 的软铝丝,网格密度每厘米 **6** 至 **7** 条铝丝)。

Rupture means the mechanical failure of a cell container or battery case induced by an internal or external cause, resulting in exposure or spillage but not ejection of solid materials.

破裂是指内部或外部原因引起的电池容器或电池组外壳机械损坏,造成内装物暴露或溢出,但无固体喷射。

Fire means that flames are emitted from the test cell or battery.

起火是指试验电池或电池组有火焰冒出。

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 10 / 18



Test Data 检测数据

Table T.1 Altitude simulation (表 T.1) 高度模拟

Test		Pre-tes	t 试验前	After tes	it 试验后			
sample status 检测样品 状态	No. 编号	v. Mass Voltage Mass Voltage	Mass loss 质量损失 (%)	Change ratio 电压比(%)	Status 结果			
First cycle,	B001	9.982	4.19	9.982	4.18	0.000	99.76	Pass 合格
fully	B002	9.945	4.18	9.944	4.18	0.010	100.00	Pass 合格
charged state	B003	9.935	4.19	9.935	4.19	0.000	100.00	Pass 合格
首次循环	B004	9.952	4.19	9.951	4.18	0.010	99.76	Pass 合格
满电状态	B005	9.957	4.18	9.957	4.18	0.000	100.00	Pass 合格
25th cycle,	B006	9.971	4.19	9.971	4.19	0.000	100.00	Pass 合格
fully	B007	9.974	4.19	9.974	4.19	0.000	100.00	Pass 合格
charged state	B008	9.965	4.18	9.965	4.18	0.000	100.00	Pass 合格
25 次循环	B009	9.938	4.19	9.936	4.19	0.020	100.00	Pass 合格
满电状态	B010	9.980	4.19	9.980	4.18	0.000	99.76	Pass 合格

Notes 注释:

After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. And change ratio is not less than 90 %. 检测后,样品无<mark>渗漏、无排气、无解体、无破裂和无起火。电压比不小</mark>于 90 %。

Table T.2 Thermal test (表 T.2) 温度试验

Test		Pre-tes	t 试验前	式验前 After test 试验后				
sample status 检测样品 状态	No. 编号	Mass 质量 (g)	Voltage 电压 (V)	Mass 质量 (g)	Voltage 电压 (V)	Mass loss 质量损失 (%)	Change ratio 电压比(%)	Status 结果
First cycle,	B001	9. <mark>982</mark>	4.18	9.974	4.14	0.080	99.04	Pass 合格
fully	B002	9. <mark>944</mark>	4.18	9.938	4.15	0.060	99.28	Pass 合格
charged state	B003	9. <mark>935</mark>	4.19	9.932	4.15	0.030	99.05	Pass 合格
首次循环	B004	9.951	4.18	9.946	4.13	0.050	98.80	Pass 合格
满电状态	B005	9.957	4.18	9.948	4.15	0.090	99.28	Pass 合格
25th cycle,	B006	9.971	4.19	9.970	4.14	0.010	98.81	Pass 合格
fully	B007	9.974	4.19	9.967	4.15	0.070	99.05	Pass 合格
charged state	B008	9.965	4.18	9.963	4.14	0.020	99.04	Pass 合格
25 次循环	B009	9.936	4.19	9.927	4.14	0.091	98.81	Pass 合格
满电状态	B010	9.980	4.18	9.976	4.15	0.040	99.28	Pass 合格

Notes 注释:

After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. And change ratio is not less than 90 %. 检测后,样品无渗漏、无排气、无解体、无破裂和无起火。电压比不小于 90 %。

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 11 / 18



Table T.3 Vibration (表 T.3) 振动

Test		Pre-test 试验前		After test 试验后				
sample status 检测样品 状态	No. 编号	Mass 质量 (g)	Voltage 电压 (V)	Mass 质量 (g)	Voltage 电压 (V)	Mass loss 质量损失 (%)	Change ratio 电压比(%)	Status 结果
First cycle,	B001	9.974	4.14	9.973	4.14	0.010	100.00	Pass 合格
fully	B002	9.938	4.15	9.938	4.14	0.000	99.76	Pass 合格
charged state 首次循环 满电状态	B003	9.932	4.15	9.932	4.15	0.000	100.00	Pass 合格
	B004	9.946	4.13	9.946	4.13	0.000	100.00	Pass 合格
	B005	9.948	4.15	9.948	4.14	0.000	99.76	Pass 合格
25th cycle, fully charged state 25 次循环 满电状态	B006	9.970	4.14	9.968	4.14	0.020	100.00	Pass 合格
	B007	9.967	4.15	9.967	4.15	0.000	100.00	Pass 合格
	B008	9.963	4.14	9.963	4.14	0.000	100.00	Pass 合格
	B009	9.927	4.14	9.927	4.14	0.000	100.00	Pass 合格
	B010	9.976	4.15	9.975	4.15	0.010	100.00	Pass 合格

Notes 注释:

After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. And change ratio is not less than 90 %. 检测后,样品无渗漏、无排气、无解体、无破裂和无起火。电压比不小于 90 %。

Table T.4 Shock (表 T.4) 冲击

Test	No. 编号	Pre-test 试验前		After test 试验后				
sample status 检测样品 状态		Mass 质量 (g)	Voltage 电压 (V)	Mass 质量 (g)	Voltage 电压 (V)	Mass loss 质量损失 (%)	Change ratio 电压比(%)	Status 结果
First cycle,	B001	9. <mark>973</mark>	4.14	9.973	4.14	0.000	100.00	Pass 合格
fully	B002	9. <mark>938</mark>	4.14	9.938	4.14	0.000	100.00	Pass 合格
charged state 首次循环 满电状态	B003	9. <mark>932</mark>	4.15	9.931	4.14	0.010	99.76	Pass 合格
	B004	9. <mark>946</mark>	4.13	9.946	4.13	0.000	100.00	Pass 合格
	B005	9.948	4.14	9.948	4.14	0.000	100.00	Pass 合格
25th cycle, fully charged state 25 次循环 满电状态	B006	9.968	4.14	9.968	4.14	0.000	100.00	Pass 合格
	B007	9.9 <mark>67</mark>	4.15	9.965	4.15	0.020	100.00	Pass 合格
	B008	9.963	4.14	9.962	4.13	0.010	99.76	Pass 合格
	B009	9.927	4.14	9.927	4.14	0.000	100.00	Pass 合格
	B010	9.975	4.15	9.975	4.14	0.000	99.76	Pass 合格

Notes 注释:

After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. And change ratio is not less than 90 %. 检测后,样品无渗漏、无排气、无解体、无破裂和无起火。电压比不小于 90 %。

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 12 / 18



Table T.5 External short circuit (表 T.5) 外部短路

Test sample status 检测样品状态	No. 编号	Maximum external temperature (°C) 表面最高温度(°C)	Status 结果
	B001	57.2	Pass 合格
First cycle, fully	B002	57.3	Pass 合格
charged state	B003	57.4	Pass 合格
首次循环满电状态	B004	57.5	Pass 合格
	B005	57.2	Pass 合格
	B006	57.1	Pass 合格
25th cycle, fully	B007	57.0	Pass 合格
charged state	B008	57.3	Pass 合格
25 次循环满电状态	B009	57.5	Pass 合格
	B010	57.4	Pass 合格

Notes 注释:

Test sample external temperature does not exceed 170°C and there is no disassembly, no rupture and no fire during the test and within six hours after the test.

检测样品表面温度不超过 170 °C,检测中与检测后 6 小时内无解体、无破裂、无起火。

Table T.6 Crush (表 T.6) 挤压

Test sample status 检测样品状态	No. 编号	Maximum external temperature (°C) 表面最高温度(°C)	Status 结果
	C001	24.4	Pass 合格
First cycle, 50%	C002	24.2	Pass 合格
charged state	C003	24.1	Pass 合格
首次循环 50%充电状态	C004	24.3	Pass 合格
	C005	24.5	Pass 合格
	C006	24.5	Pass 合格
25th cycle, 50%	C007	24.4	Pass 合格
charged state	C008	24.2	Pass 合格
25次循环50%充电状态	C009	24.3	Pass 合格
	C010	24.1	Pass 合格

Notes 注释:

Test sample external temperature does not exceed 170°C and there is no disassembly, no rupture and no fire during the test and within six hours after the test.

检测样品表面温度不超过 170℃, 检测中与检测后 6 小时内无解体、无破裂、无起火。

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 13 / 18



Table T.7 Overcharge (表 T.7) 过度充电

Test sample status 检测样品状态	No. 编号	Status 结果
	B011	Pass 合格
First cycle, fully charged state	B012	Pass 合格
首次循环满电状态	B013	Pass 合格
	B014	Pass 合格
	B015	Pass 合格
25th cycle, fully charged state	B016	Pass 合格
25 次循环满电状态	B017	Pass 合格
	B018	Pass 合格

Notes 注释:

There is no disassembly and no fire during the test and within seven days after the test. 样品在检测中和检测后 7 天内无解体、无起火。

Table T.8 Forced discharge (表 T.8) 强制放电

Test sample status	No.	Status
检测样品状态	编号	结果
	C011	Pass 合格
	C012	Pass 合格
	C013	Pass 合格
	C014	Pass 合格
First cycle, fully discharged state	C015	Pass 合格
首次循环完全放电状 <mark>态</mark>	C016	Pass 合格
	C017	Pass 合格
	C018	Pass 合格
	C019	Pass 合格
	C020	Pass 合格
	C021	Pass 合格
	C022	Pass 合格
	C023	Pass 合格
	C024	Pass 合格
25th cycle, fully discharge <mark>d state</mark>	C025	Pass 合格
25 次循环完全放电状态	C026	Pass 合格
	C027	Pass 合格
	C028	Pass 合格
	C029	Pass 合格
	C030	Pass 合格

Notes 注释:

There is no disassembly and no fire during the test and within seven days after the test. 样品在检测中和检测后 7 天内无解体、无起火。


101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 14 / 18




Photos of Samples

样品照片



Picture 1. Front view of battery 图片 1. 电池组前视图




Picture 2. Back view of battery 图片 2. 电池组后视图

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104


400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 15 / 18







Picture 3. Front view of cell 图片 3. 电池前视图



Picture 4. Back view of cell 图片 4. 电池后视图

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 16 / 18





Picture 5. Front view of Protection board 图片 5. 保护板前视图



Picture 6. Back view of Protection board 图片 6. 保护板后视图

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 17 / 18

Important

注意事项

- 1. The test report is invalid if it is not affixed the official seal of the laboratory to it. 检测报告无本实验室公章(或检验检测专用章)无效。
- 2. Copies of the test report without the official seal of the laboratory are invalid. 复制检测报告未重新加盖本实验室公章(或检验检测专用章)无效。
- 3. It is forbidden to copy the test report partially without the written approval of the laboratory.

未经本实验室书面批准不得部分复制检测报告。

4. The test report is invalid without the signatures of Approver, Reviewer and Testing engineer.

检测报告无检测、审核、批准人签名无效。

5. The test report is invalid if it is blotted out.

检测报告涂改无效。

6. Objections to the test report must be submitted to CMC Testing International (Shenzhen)
Co., Ltd. within 15 days.

对检测报告若<mark>有异议,应于收到报告之日起十五天内向众检检验认证</mark>(深圳)有限公司提出。

7. The test report is valid for the tested samples only.

本检测报告仅对检测样品负责。

8. As for the Verdict, "--" means "no need for judgment", "P" means "pass", "F" means "fail" and "N/A" means "not applicable".

判定栏中"--"表示"不需要判定","P"表示"通过","F"表示"不通过","N/A"表示"不适用"。

*** End of Report ***

*** 报告结束 ***

Testing laboratory: CMC Testing International (Shenzhen) Co., Ltd.

检测单位: 众检检验认证 (深圳) 有限公司

Address: 101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China