





UN38.3 TEST REPORT UN38.3 检测报告

Report No.:

报告编号:

CMC241128051

Name of Goods:

Cylindrical lithium-ion rechargeable cell

物品名称: 圆柱形可充电锂离子电芯

Model:

IMR18650-1200mAh 型号:

Type:

3.7V 1200mAh 4.44Wh 规格:

Client:

Xinxiang Hongli Supply Source Technology Co., Ltd. 新乡市弘力电源科技有限公司 委托单位:

Classification

of test:

检测类别:

Commission Test

委托测试

Tested by 主检人:

Riley Xiao \$ 3

Approved by 批准人:

(Technical Director 技术总监)

(Testing Engineer 测试工程师)

Riley Xiao 肖兰

Dylan Dou 窦明波

Dylan Dou 塞胸 Inspected by 审核人: (Department Manager 部门经理)

Seal of CMC:

CMC 印章:

Date of Issue:

签发日期:

2024.12.24

CMC Testing International (Shenzhen) Co., Ltd.

众检检验认证 (深圳) 有限公司

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104 Version: A/2.5

400-1668-320 info@cmczj-lab.com 1 / 16 www.cmczj-lab.com



TEST REPORT 检测报告

		JTT (V.1	7 P H					
Name of Goods 物品名称	Cylindrical lithic rechargeable c 圆柱形可充电链	ell	Model 型号	IMR18650-1	IMR18650-1200mAh			
Commissioner 委托单位		Xinxiang Hongli Supply Source Technology Co., Ltd. 新乡市弘力电源科技有限公司						
Commissioner's Address 委托单位地址	Xinxiang City, I	West section of Xinglong Road, Xinxiang Economic Development Zone, Xinxiang County, Xinxiang City, Henan Province 可南省新乡市新乡县新乡经济开发区兴隆路西段						
Manufacturer 生产厂	997	Xinxiang Hongli Supply Source Technology Co., Ltd. 新乡市弘力电源科技有限公司						
Manufacturer's Address 生产厂地址	Xinxiang City, I	West section of Xinglong Road, Xinxiang Economic Development Zone, Xinxiang County, Xinxiang City, Henan Province 河南省新乡市新乡县新乡经济开发区兴隆路西段						
Manufacturer's Contact Telephone 生产厂联系电话	+86-186	637376487	E-mail 邮箱 Web 网址	760172564@qq.com				
Trade Mark/ identification 商标/识别码		Shape 形状	Cylinder 圆柱体	Size 尺寸 (DxH)	(18.2×65.0)mm			
Nominal Voltage 标称电压	3.7V	Charge Voltage 充电电压	4 .2V	Rated Capacity 额定容量	1200mAh			
Cell Model 电池型号	IMR <mark>18650-12 Cell Nominal Voltage 00mAh Limitation </mark>		3.7V	Cell Rated Capacity 电池额定容量	1200mAh			
Cells Number 电池数量	1PC	Sample Receiving Date 样品接收日期	2024.11.28	2024.11.28 Testing Date 则试日期 2024.12.12 2024.12.12				
Test conclusion 检测结论	ST/SG/AC.10/	s passed the test ite I1/Rev.7/ Amend.1 \$ 品符合联合国《试验和	Subsection 38.3					

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 2 / 16



Test Standard 检测标准

UN "Manual of Tests and Criteria" ST/SG/AC.10/11/Rev.7/Amend.1 Subsection 38.3

联合国《试验和标准手册》 (第7修订版 修正1) 38.3 节

Description and illustration of the sample: The sample's status is good.

样品说明及描述:样品状况良好。

Test item	Sample No.	State			
检测项目	样品编号	状态	备注		
	C001~C005	At first cycle, in fully charged states 第 1 个充电周期,完全充电状态			
Test 1 ~ Test 5	C006~C010	After 25 cycles ending in fully charged states 第 25 个充电周期,完全充电状态			
T 10	C011~C015	At first cycle at 50% of the design rated capacity 第1个充放电周期 50%设计额定容量状态			
Test 6	C016~C020	C016~C020 After 25 cycle at 50% of the design rated capacity 第25个充放电周期 50%设计额定容量状态			
-4-	-	-			
Test 7					
- 10	C021~C030	At first cycle in fully discharged states 第1个充放电周期,完全放电状态			
Test 8	C031~C040	After 25 cycles ending in fully discharged states 第25个充放电周期,完全放电状态			

CXXX is used as the samp<mark>le number of cell</mark>s SN241128051CXXX, "X" is 0~9.

CXXX 代表电芯样板编号 SN241128051CXXX, X=0~9。

Description of the deviation from the standard, if any:

检测结果不符合标准项的说明:

Test environment conditions: Ambient temperature: 25 °C ±5 °C, Ambient humidity: 45%-75%

检测环境条件: 环境温度: **25**℃±**5**℃; 环境湿度: **45%-75%**

Remarks:

备注:

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 3 / 16



		Report No.: CMC2411	20031
Olama	ST/SG/AC.10/11/Rev.7/Amend.1 Subset		Vandiat
Clause 章节	Requirements 标准要求	Result 测试结果	Verdict 判定
38.3.4	Procedure 检测步骤		
38.3.4.1	Test 1: Altitude simulation 检测 1: 高度模拟		
	Test cells and batteries shall be stored at a pressure of 11.6kPa at ambient temperature (20±5°C). 将电池和电池组在温度为 20±5°C,大气压力为不大于 11.6kPa		
	Requirements 标准要求: 1) Cells and batteries Mass loss limit reference: Table 38.3.1 样品质量损失限值参考:表 38.3.1 2) Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后开路电压应不低于试验前开路电压的 90%,此要求不适用于完全放完电的电池或电池组。 3) No leakage, no venting, no disassembly, no rupture and no fire.样品(电池)应无渗漏、无排气、无解体、无破裂以及无起火现象的发生。	The samples C001~C010: No leakage, no venting, no disassembly, no rupture and no fire. 编号为 C001~C010 的样品: 无渗漏、无排气、无解体、无破裂以及无起火现象。 The data is shown in Test T.1 数据见表 T.1	Pass 合格
38.3.4.2	Test 2: Thermal test 检测 2: 温度试验 Test cells and batteries are to be stored for 电池和电池组存储条件如下: 1) For small cells and batteries: one temperature cycle: 72±2°C 对于小型电池和电池组: 一次温度循环为 72±2°C (6h) ~ -40±2°E For large cells and batteries: one temperature cycle: 72±2°C (1对于大型电池和电池组: 一次温度循环为 72±2°C (12h) ~ -40±2°C The maximum time interval between test temperature extrer温度转换最大间隔时间为 30min。 3) This procedure is to be repeated 10 times. 重复 10 次循环。4) after which all test cells and batteries are to be stored for 24 (20±5°C). 循环结束后,电池和电池组在 20±5°C 的条件下搁置 Requirement 标准要求: 1) Cells and batteries Mass loss limit reference: Table 38.3.1 样品质量损失限值参考:表 38.3.1 2) Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后开路电压应不低于试验前开路电压的 90%,此要求不适用于完全放完电的电池和电池组。3) No leakage, no venting, no disassembly, no rupture and no	C (6h) (2h) ~ -40±2°C (12h) (2°C (12h) (nes is 30minutes. hours at ambient temperature	Pass 合格

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 4 / 16



		Report No.: CMC2411	28051
Clause 章节	ST/SG/AC.10/11/Rev.7/Amend.1 Subse Requirements 标准要求	ction 38.3 Result 测试结果	Verdict 判定
	-	Result 测试结果 wibration machine. ep between 7Hz and 200Hz dz 为一个循环,一个循环持续 of 1gn is maintained until 18Hz n total excursion) and the pproximately 50Hz). A peak creased to 200Hz. 不变,直到达到 18Hz。然后将 gn的峰值加速度(大约 50Hz)。 ntained until 18Hz is reached. resion) and the frequency ely 25Hz). A peak acceleration 10Hz. 直到达到 18Hz。然后将振幅保	
	保持 2gn 的峰值加速度,直到频率增加到 200Hz。 4) This cycle repeated 12 times for a total of 3 hours for each comounting position of the cell. One of the directions of vibration terminal face. 以振动的其中一个方向必须是垂直样品极性,对每个电池从三个每个方向 3 个小时,共 9 小时。 Requirements 标准要求: 1) Cells and batteries Mass loss limit reference: Table 38.3.1 样品质量损失限值参考:表 38.3.1 2) Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后开路电压应不低于试验前开路电压的 90%,此要求不适用于完全放完电的电池和电池组。 3) No leakage, no venting, no disassembly, no rupture and no fire. 样品(电池)应无渗漏、无排气、无解体、无破裂以及无起火现象的发生。	of three mutually perpendicular must be perpendicular to the	

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 5 / 16



ST/SG/AC.10/11/Rev.7/Amend.1 Subsection 38.3									
Clause 章节	RequirementsResult标准要求测试结果								
38.3.4.4	Test 4: Shock 检测 4: 冲击								
	1) Test cells and batteries shall be secured to the testing machine. 以稳固的托架固定住每个电池和电池组样品的全部配件表面。 2) Each cell shall be subjected to a half-sine shock of peak acceleration of 150gn and pulse duration of 6 milliseconds. Large cells may be subjected to a half-sine shock of peak acceleration of 50gn and pulse duration of 11 milliseconds. 对每个电池以峰值为 150gn的半正弦的加速度撞击,脉冲持续 6ms,大型电池须经受最大加速度 50gn和脉冲持续时间 11ms 的半正弦波冲击。 Small batteries shall be subjected to a half-sine shock of peak acceleration of 150gn (or								
	Acceleration $(g_n) = \sqrt{\frac{(100850)}{mass}}$, which is smaller) aneration of $50g_n$	(or Acceleration $(g_n) = \sqrt{\frac{30000}{mass}}$,							
	which is smaller) and pulse dud pulse duration of 6 millisecond	s, large batterie <mark>s</mark> sh <mark>all</mark> be							
	subjected to a half-sine of peak accelration of 11 milliseconds.								
	对每个电池以峰值为 150g _n (或与√(100850)中的较小值)的半正弦的加速度撞击,脉冲持续 6ms,								
	大型电池须经受最大加速度 50gn(或与√(30000)中的较小值)和脉冲持续时间 11ms 的半正弦波								
	冲击。 3) Each cell or battery shall be subjected to three shocks in the positive direction followed by three shocks in the negative direction of three mutually perpendicular mounting positions of the cell or battery for a total of 18 shocks. 每个电池或电池组须在三个互相垂直的电池安装方位的正方向经受三次冲击,接着在反方向经受三次冲击,总共经受 18 次冲击。								
	Requirements 标准要求: 1) Cells and batteries Mass loss limit: ≤0.2%. 样品质量损失≤0.2% 2) Open circuit voltage not less than 90%, The requirement relating to voltage is not applicable to test cells and batteries at full discharged states. 样品试验后开路电压应不低于试验前开路电压的 90%,此要求不适用于完全放完电的电池或电池组。 3) No leakage, no venting, no disassembly, no rupture and no fire. 样品(电池)应无渗漏、无排气、无解体、无破裂以及无起火现象的发生。	The samples C001~C010: No leakage, no venting, no disassembly, no rupture and no fire. 编号为 C001~C010 的样品: 无渗漏、无排气、无解体、无破裂以及无起火现象。 The data is shown in Table T.4 数据见表 T.4							

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 6 / 16



ST/SG/AC.10/11/Rev.7/Amend.1 Subsection 38.3						
Clause 章节	Requirements 标准要求	Result 测试结果	Verdict 判定			
38.3.4.5	Test 5: External Short Circuit 检测 5: 外部短路					
	1) The cell or battery to be tested shall be heated for a period of homogeneous stabilized temperature 57±4°C. 加热电池或电池组样品直到温度稳定在 57±4°C 2) The cell or battery shall be subjected to a short circuit condit resistance of less than 0.1 ohm at 57±4°C, This short circuit co one hour after the cell or battery external case temperature has 将样品正负极用小于 0.1Ω 的总电阻回路进行短路,样品的外表短路状态 1 小时以上。 3) The cell or battery must be observed for a further six hours f对电池或电池组必须进一步观察 6 个小时才能下结论。	tion with a total external ndition is continued for at least s returned to 57±4°C. 温度恢复到 57±4°C 之后保持	Pass 合格			
	Requirements 标准要求: 1) Cells external temperature not exceed 170°C. 电池的最高表面温度应不超过 170°C。 2) No disassembly, no rupture and no fire during the test and within six hours after the test. 测试中与测试后 6 小时内无解体、无破裂、无起火。 The samples C001~C010: No disassembly, no rupture and no fire. 编号为 C001~C010 的样品: 无解体、无破裂以及无起火现象。 The data is shown in Table T.5 数据见表 T.5					
8.3.4.6	Test 6: Impact / Crush 检测 6: 撞击/挤压		Pass 合格			
	Impact (applicable to cylindrical cells not less than 18mm in dia 撞击(适用于直径不小于 18 毫米的圆柱形电池) 1) This test sample cell or component cell is to be placed on a 将试验样品用的电池或元件电池放在一个平坦光滑的平面上 2) A 15.8 mm diameter bar is to be placed across the center of be dropped from a height of 61±2.5cm onto the sample. 将一直径为 15.8mm 的不锈钢圆棒横过电池中部放置后,将一质的高度落向样品。 3) The test sample is to be impacted with its longitudinal axis proper pendicular to the longitudinal axis of the 15.8mm ± 0.1mm carross the center of the test sample. Each sample is to be sub接受撞击的试样,纵轴应与平坦的表面平行并与横放在试样中心的纵轴垂直。每一个试样只经受一次撞击。 Requirements 标准要求: 1) Cells external temperature not exceed 170°C. 电池的最高表面温度应不超过 170°C。 2) No disassembly, no rupture and no fire during the test and within six hours after the test.	flat smooth surface. the sample, A 9.1kg mass is to 量为 9.1kg 的物体从 61±2.5cm arallel to the flat surface and diameter curved surface lying jected to only a single impact.	Pass 合格			

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

T.6 数据见表 T.6

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 7 / 16



	ST/SG/AC.10/11/Rev.7/Amend.1 Subsection 38.3					
Clause 章节	RequirementsResult标准要求测试结果	Verdict 判定				
	Crush (applicable to prismatic, pouch, coin/button cells and cylindrical cells less than 18mm in diameter). 挤压(适用于棱柱形、袋装、硬币/纽扣电池和直径小于 18 毫米的圆柱形电池)。					
	1) A cell or component cell is to be crushed between two flat surfaces. The crushing is to be gradual with a speed of approximately 1.5cm/s at the first point of contact. The crushing is to be continued until the first of the three options below is reached. 将电池或元件电池放在两个平面之间挤压,挤压力度逐渐加大,在第一个接触点上的速度大约为 1.5 厘米/秒。挤压持续进行,直到出现以下三种情况之一: (a) The applied force reaches 13kN ± 0.78kN. 施加的力达到 13 千牛顿±0.78 千牛顿。 (b) The voltage of the cell drops by at least 100mV. 电池的电压下降至少 100 毫伏。 (c) The cell is deformed by 50% or more of its original thickness. 电池变形达原始厚度的 50%或以上。 2). A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surfaces. For cylindrical cells, the crush force shall be applied perpendicular to the longitudinal axis. 棱柱形或袋装电池应从最宽的一面施压。纽扣/硬币形电池应从其平坦表面施压。圆柱形电池应从与纵轴垂直的方向施压。 Requirements 标准要求: 1) Cells external temperature not exceed 170°C. 电池的最高表面温度应不超过 170°C。 2) No disassembly, no rupture and no fire during the test and within six hours after the test. 测试中与测试后 6 小时内无解体、无破裂、无起火。	N/A 不适用				

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 8 / 16



		Report No.: CMC2411	28051		
	ST/SG/AC.10/11/Rev.7/Amend.1 Subsect	tion 38.3			
Clause 章节	•	Result 测试结果	Verdict 判定		
38.3.4.7	Test 7: Overcharge 检测 7: 过度充电				
	1) The charge current shall be twice the manufacturer's recommon charge current. 以制造商建议的最大持续充电电流的两倍对样品2) The minimum voltage of the test shall be as follows: 试验的最a) When the manufacturer's recommended charge voltage is no minimum voltage of the test shall be the lesser of two times the the battery or 22V.制造商建议的充电电压不大于 18V 时,试验的最小电压应是电池经两者中的较小者。b) when the manufacturer's recommended charge voltage is movoltage of the test shall be 1.2 times the maximum charge voltage 制造商建议的充电电压大于 18V 时,试验的最小电压应为最大充3) Tests are to be conducted at ambient temperature 20±5°C, Th 24 hours. 试验应在环境温度(20±5°C)下进行。进行试验的时间Requirements 标准要求: No disassembly and no fire during the test and within seven days after the test.	充电。 技小电压如下: It more than 18V, the maximum charge voltage of 组最大充电电压的两倍或 22V re than 18V, the minimum ge. 电电压的 1.2 倍。 e duration of the test shall be	N/A 不适用		
	试验过程中和试验后7天内无解体,无起火。				
38.3.4.8	Test 8: Forced <mark>discharge</mark> 检测 8: 强制放 <mark>电</mark>				
	Each cell shall be forced discharged at ambient temperature by 12V D.C. power supply at an initial current equal to the maximur by the manufacturer. 每个电池应在环境温度(20±5°C)下与 12V 直流电源串联在起始放电电流的条件下强制放电。	m discharge current specified			
	The specified discharge current is to be obtained by connecting a resistive load of the appropriate size and rating in series with the test cell. Each cell shall be forced discharged for a time interval (in hours) equal to its rated capacity divided by the initial test current (in ampere). 将适当大小和额定值的电阻负荷与试验电池串联,计算得出给定的放电电流。对每个电池进行强制放电,放电时间(小时)应等于其额定容量除以初始试验电流(安培)。				
	No disassembly and no fire during the test and within seven	The samples C021~C040: no disassembly and no fire. 编号为 C021~C040 的样品:			

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

试验过程中和试验后7天内无解体,无起火。

400-1668-320 info@cmczj-lab.com 9 / 16 www.cmczj-lab.com

无解体、无起火现象。 The data is shown in Table

T.8

数据见表 T.8



ST/SG/AC.10/11/Rev.7/Amend.1 Subsection 38.3

General terms and definitions 一般术语与定义

Table 38.3.1: Mass loss limit 表 38.3.1: 质量损失限值

Mass M of cell or battery	Mass loss limit
电池或电池组质量 M	质量损失限值
M < 1 g	0.5%
1 g ≤ M ≤75 g	0.2%
M > 75 g	0.1%

In order to quantify the mass loss, the following procedure is provided:

Mass loss (%) = $(M_1 - M_2)/M_1 \times 100$

质量损失的量化值,可用以下公式计算:

质量损失(%) = $(M_1 - M_2)/M_1 \times 100$

Where M1 is the mass before the test and M2 is the mass after the test. When mass loss does not exceed the values in Table 38.3.1, it shall be considered as "no mass loss".

式中: M1 是试验前的质量, M2 是试验后的质量。如果质量损失不超过表 38.3.1 所列的数值, 应视为"无质量损失"。

Leakage means the visible escape of electrolyte or other material from a cell or battery or the loss of material (except battery casing, handling devices or labels) from a cell or battery such that the loss of mass exceeds the values in Table 38.3.1.

渗漏是指可以看到的电解<mark>液或者其他物质从电</mark>池或电池组中漏出,或电池或电池组中的物质损失(不包括电池外壳、搬运装置、或标签),质量损失超过表 **38.3.1** 所列的数值。

Venting means the release of excessive internal pressure from a cell or battery in a manner intended by design to preclude rupture or disassembly.

排气是指按设计方式释放电池或电池组内部过高的压力,防止其破裂或解体。

Disassembly means a vent or rupture where solid matter from any part of a cell or battery penetrates a wire mesh screen (annealed aluminium wire with a diameter of 0.25 mm and grid density of 6 to 7 wires per cm) placed 25 cm away from the cell or battery.

解体是指排气或破裂使<mark>电池或电池组任何部分的固体物质穿过放</mark>在离电池或电池 **25 cm** 处的丝网筛(直径 **0.25 mm** 的软铝丝,网格密度每厘米 **6** 至 **7** 条铝丝)。

Rupture means the mechanical failure of a cell container or battery case induced by an internal or external cause, resulting in exposure or spillage but not ejection of solid materials.

破裂是指内部或外部原因引起的电池容器或电池组外壳机械损坏,造成内装物暴露或溢出,但无固体喷射。

Fire means that flames are emitted from the test cell or battery.

起火是指试验电池或电池组有火焰冒出。

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 10 / 16



Test Data 检测数据

Table T.1 Altitude simulation (表 T.1) 高度模拟

Test sample status 检测样品 状态		Pre-test 试验前		After test 试验后				
	No. 编号	Mass 质量 (g)	Voltage 电压 (V)	Mass 质量 (g)	Voltage 电压 (V)	Mass loss 质量损失 (%)	Change ratio 电压比(%)	Status 结果
First cycle,	C001	34.205	4.18	34.204	4.18	0.003	100.00	Pass 合格
fully	C002	34.196	4.19	34.196	4.18	0.000	99.76	Pass 合格
charged state	C003	34.179	4.18	34.179	4.17	0.000	99.76	Pass 合格
首次循环	C004	34.124	4.19	34.124	4.19	0.000	100.00	Pass 合格
满电状态	C005	34.201	4.19	34.198	4.19	0.009	100.00	Pass 合格
25th cycle,	C006	34.188	4.18	34.188	4.18	0.000	100.00	Pass 合格
fully	C007	34.179	4.19	34.179	4.19	0.000	100.00	Pass 合格
charged state	C008	34.162	4.18	34.160	4.18	0.006	100.00	Pass 合格
25 次循环	C009	34.122	4.19	34.122	4.19	0.000	100.00	Pass 合格
满电状态	C010	34.156	4.19	34.156	4.18	0.000	99.76	Pass 合格

Notes 注释:

After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. And change ratio is not less than 90 %. 检测后,样品无渗漏、无排气、无解体、无破裂和无起火。电压比不小于 90 %。

Table T.2 Thermal test (表 T.2) 温度试验

Test sample status 检测样品 状态		Pre-test 试验前		After tes	After test 试验后			
	No. 编号	Mass 质量 (g)	Voltage 电压 (V)	Mass 质量 (g)	Voltage 电压 (V)	Mass loss 质量损失 (%)	Change ratio 电压比(%)	Status 结果
First cycle,	C001	3 <mark>4.204</mark>	4.18	34.197	4.15	0.020	99.28	Pass 合格
fully	C002	34.196	4.18	34.192	4.13	0.012	98.80	Pass 合格
charged state	C003	34.179	4.17	34.169	4.13	0.029	99.04	Pass 合格
首次循环	C004	34.124	4.19	34.116	4.15	0.023	99.05	Pass 合格
满电状态	C005	34.198	4.19	34.186	4.14	0.035	98.81	Pass 合格
25th cycle,	C006	34.188	4.18	34.179	4.15	0.026	99.28	Pass 合格
fully	C007	34.179	4.19	34.168	4.15	0.032	99.05	Pass 合格
charged state	C008	34.160	4.18	34.154	4.14	0.018	99.04	Pass 合格
25 次循环	C009	34.122	4.19	34.115	4.14	0.021	98.81	Pass 合格
满电状态	C010	34.156	4.18	34.151	4.13	0.015	98.80	Pass 合格

Notes 注释:

After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. And change ratio is not less than 90 %. 检测后,样品无渗漏、无排气、无解体、无破裂和无起火。电压比不小于 90 %。

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 11 / 16



Table T.3 Vibration (表 T.3) 振动

Test	No. 编号	Pre-test 试验前		After test 试验后				
sample status 检测样品 状态		Mass 质量 (g)	Voltage 电压 (V)	Mass 质量 (g)	Voltage 电压 (V)	Mass loss 质量损失 (%)	Change ratio 电压比(%)	Status 结果
First cycle,	C001	34.197	4.15	34.197	4.14	0.000	99.76	Pass 合格
fully	C002	34.192	4.13	34.192	4.13	0.000	100.00	Pass 合格
charged state 首次循环 满电状态	C003	34.169	4.13	34.168	4.13	0.003	100.00	Pass 合格
	C004	34.116	4.15	34.116	4.15	0.000	100.00	Pass 合格
	C005	34.186	4.14	34.184	4.14	0.006	100.00	Pass 合格
25th cycle, fully charged state 25 次循环 满电状态	C006	34.179	4.15	34.179	4.15	0.000	100.00	Pass 合格
	C007	34.168	4.15	34.168	4.14	0.000	99.76	Pass 合格
	C008	34.154	4.14	34.154	4.14	0.000	100.00	Pass 合格
	C009	34.115	4.14	34.115	4.13	0.000	99.76	Pass 合格
	C010	34.151	4.13	34.148	4.13	0.009	100.00	Pass 合格

Notes 注释:

After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. And change ratio is not less than 90 %. 检测后,样品无渗漏、无排气、无解体、无破裂和无起火。电压比不小于 90 %。

Table T.4 Shock (表 T.4) 冲击

Test	No. 编号	Pre-test 试验前		After test 试验后				
sample status 检测样品 状态		Mass 质量 (g)	Voltage 电压 (V)	Mass 质量 (g)	Voltage 电压 (V)	Mass loss 质量损失 (%)	Change ratio 电压比(%)	Status 结果
First cycle,	C001	3 <mark>4.197</mark>	4.14	34.197	4.14	0.000	100.00	Pass 合格
fully	C002	34.192	4.13	34.190	4.13	0.006	100.00	Pass 合格
charged state	C003	34.168	4.13	34.168	4.13	0.000	100.00	Pass 合格
首次循环	C004	34.116	4.15	34.116	4.14	0.000	99.76	Pass 合格
满电状态	C005	34.184	4.14	34.184	4.14	0.000	100.00	Pass 合格
25th cycle, fully charged state 25 次循环 满电状态	C006	34.179	4.15	34.179	4.14	0.000	99.76	Pass 合格
	C007	34.168	4.14	34.167	4.14	0.003	100.00	Pass 合格
	C008	34 <mark>.154</mark>	4.14	34.154	4.13	0.000	99.76	Pass 合格
	C009	34.115	4.13	34.115	4.13	0.000	100.00	Pass 合格
	C010	34.148	4.13	34.145	4.13	0.009	100.00	Pass 合格

Notes 注释:

After the test, there is no leakage, no venting, no disassembly, no rupture and no fire. And change ratio is not less than 90 %. 检测后,样品无渗漏、无排气、无解体、无破裂和无起火。电压比不小于 90 %。

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 12 / 16



Table T.5 External short circuit (表 T.5) 外部短路

Test sample status 检测样品状态	No. 编号	Maximum external temperature (°C) 表面最高温度(°C)	Status 结果
	C001	92.5	Pass 合格
First cycle, fully	C002	95.2	Pass 合格
charged state	C003	94.6	Pass 合格
首次循环满电状态	C004	98.5	Pass 合格
	C005	89.6	Pass 合格
	C006	90.2	Pass 合格
25th cycle, fully	C007	93.9	Pass 合格
charged state	C008	91.8	Pass 合格
25 次循环满电状态	C009	97.4	Pass 合格
	C010	96.2	Pass 合格

Notes 注释:

Test sample external temperature does not exceed 170°C and there is no disassembly, no rupture and no fire during the test and within six hours after the test.

检测样品表面温度不超过 170°C,检测中与检测后 6 小时内无解体、无破裂、无起火。

Table T.6 Impact (表 T.6)撞击

Test sample status 检测样品状态	No. 编号	Maximum external temperature (°C) 表面最高温度(°C)	Status 结果
	C011	89.1	Pass 合格
First cycle, 50%	C012	95.2	Pass 合格
charged state	C013	94.6	Pass 合格
首次循环 50% 充电状态	C014	98.5	Pass 合格
	C015	93.7	Pass 合格
	C016	91.9	Pass 合格
25th cycle, 50%	C017	97.7	Pass 合格
charged state	C018	92.8	Pass 合格
25次循环50%充电状态	C019	89.9	Pass 合格
	C020	96.2	Pass 合格

Notes 注释:

Test sample external temperature does not exceed 170°C and there is no disassembly, no rupture and no fire during the test and within six hours after the test.

检测样品表面温度不超过170℃,检测中与检测后6小时内无解体、无破裂、无起火。

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 13 / 16



Table T.7 Overcharge (表 T.7) 过度充电

Not applicable 不适用

Table T.8 Forced discharge (表 T.8) 强制放电

Test sample status	No.	Status	
检测样品状态	编号	结果	
	C021	Pass 合格	
	C022	Pass 合格	
	C023	Pass 合格	
	C024	Pass 合格	
First cycle, fully discharged state	C025	Pass 合格	
首次循环完全放电状态	C026	Pass 合格	
	C027	P <mark>ass 合格</mark>	
	C028	Pass 合格	
	C029	Pass 合格	
	C030	Pass 合格	
	C031	Pass 合格	
	C032	Pass 合格	
	C033	Pass 合格	
	C034	Pass 合格	
25th cycle, fully discharged state	C035	Pass 合格	
25 次循环完全放电 <mark>状态</mark>	C036	Pass 合格	
	C037	Pass 合格	
	C038	Pass 合格	
	C039	Pass 合格	
	C040	Pass 合格	

Report No.: CMC241128051

Notes 注释:

There is no disassembly and no fire during the test and within seven days after the test.

样品在检测中和检测后7天内无解体、无起火。

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 14 / 16



Photos of Samples

样品照片



Picture 1. Front view of cell 图片 1. 电池前视图



Picture 2. Back view of cell 图片 2. 电池后视图

101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China 中国广东省深圳市宝安区福海街道和平社区荔园路恺辉茂工业园厂房 B 栋 101、104

400-1668-320 info@cmczj-lab.com www.cmczj-lab.com 15 / 16



Important

注意事项

1. The test report is invalid if it is not affixed the official seal of the laboratory to it. 检测报告无本实验室公章(或检验检测专用章)无效。

2. Copies of the test report without the official seal of the laboratory are invalid. 复制检测报告未重新加盖本实验室公章(或检验检测专用章)无效。

3. It is forbidden to copy the test report partially without the written approval of the laboratory.

未经本实验室书面批准不得部分复制检测报告。

4. The test report is invalid without the signatures of Approver, Reviewer and Testing engineer.

检测报告无检测、审核、批准人签名无效。

5. The test report is invalid if it is blotted out. 检测报告涂改无效。

6. Objections to the test report must be submitted to CMC Testing International (Shenzhen) Co., Ltd. within 15 days.

对检测报告若有异议,应于收到报告之日起十五天内向众检检验认证(深圳)有限公司提出。

7. The test report is valid for the tested samples only.

本检测报告仅对检测样品负责。

8. As for the Verdict, "--" means "no need for judgment", "P" means "pass", "F" means "fail" and "N/A" means "not applicable".

判定栏中"--<mark>"表示"不需要判定","P"表示"通过","F"</mark>表示"不<mark>通过","N/A"表示"</mark>不适用"。

*** End of Report ***

*** 报告结束 ***

Testing laboratory: CMC Testing International (Shenzhen) Co., Ltd.

检测单位: 众检检验认证 (深圳) 有限公司

Address: 101&104, Building B, Kaihuimao Industrial Park, Liyuan Road, Heping Community, Fuhai Street, Baoan District, Shenzhen, Guangdong, China