

UN38.3 测试报告

UN38.3 Test Report

样 品 名 称 : 移动电源无线充
电池容量: 5000mAh 19.25Wh

Sample name : Power bank wireless charging
Battery Capacity: 5000mAh 19.25Wh

型 号 Model : P322.90

申 请 人 : 深圳市睿格鑫电子有限公司

Applicant : Digiview Technology Limited



东莞市中认联科检测技术有限公司
Dongguan ZRLK Testing Technology Co., Ltd.



申请人信息 Applicant information	名称 Name	深圳市睿格鑫电子有限公司 Digiview Technology Limited
	地址 Address	深圳市宝安区福海街道新和社区宝安大道 6099 号星港同创汇天枢座 508-510 Room 508-510, Tian Shu Block, Xinggang Tongchuanhui, No.6099 Baoan District, Shenzhen, Guangdong, China
制造商信息 Manufacturer information	名称 Name	东莞市睿格鑫电子有限公司 DongGuan Digiview Technology Limited
	地址 Address	广东省东莞市长安镇复兴路 36 号 3 号楼 903 室 Room 903,Building B3,NO.36,Fuxing Road, Chang'an Town, Dongguan City,Guangdong Province,China.
	电话 Phone number	+86-13537155283
	邮箱地址 Email address	zly029@dg-digiview.com
	网址 Website	--
工厂信息 Factory information	名称 Name	东莞市睿格鑫电子有限公司 DongGuan Digiview Technology Limited
	地址 Address	广东省东莞市长安镇复兴路 36 号 3 号楼 903 室 Room 903,Building B3,NO.36,Fuxing Road, Chang'an Town, Dongguan City,Guangdong Province,China.
	电话 Phone number	+86-13537155283
	邮箱地址 Email address	zly029@dg-digiview.com
	网址 Website	--

样品描述及说明 General product information			
样品类型(是否可充电) Sample Type(Rechargeable or not)	☒ 是/Yes		☐ 否/No
样品信息 Sample information:			
产品名称 Product Name	移动电源无线充 Power bank wireless charging	型号 Model	P322.90
商标 Trade mark	无 N/A	样品编号 Sample No.	B1#~B18# C1#~C30#
标称电压 Nominal Voltage	5V	额定容量 Rated Capacity	5000mAh
额定能量 Rated Energy	19.25Wh	充电截止电压 Charge Cut-off Voltage	5.25V
最大充电电流 Max. Charging Current	Type-C Input: 5V $\Rightarrow$ 2.4A	标准充电电流 Standard Charging Current	Type-C Input: 5V $\Rightarrow$ 2.4A
充电截止电流 Charge Cut-off Current	--	放电终止电压 Discharge Cut-off Voltage	--
最大放电电流 Max. Discharging Current	Type-C Output: 5V $\Rightarrow$ 2.4A	标准放电电流 Standard Discharging Current	Type-C Output: 5V $\Rightarrow$ 2.4A
形状 Shape	棱柱形 Prismatic	尺寸 Size	102.9*67.8*12.0mm
样品质量 Sample Mass	135.5g	串并联方式 Connection composition of series-parallel	1S1P
电芯信息 Cell information:			
电芯型号 Cell Model	706074	标称电压 Nominal Voltage	3.85V
额定容量 Rated Capacity	5000mAh	最大放电电流 Max. Discharging Current	5000mA

样品接收日期 Accepted date	2025-06-13	测试起始日期 Test date	2025-06-13 ~ 2025-07-04
测试方法 和判定标准 Test method and criterion	联合国《试验和标准手册》（第 8 版）38.3 节 UN "Manual of Tests and Criteria" ST/SG/AC.10/11/Rev.8/Subsection 38.3		
测试项目 Test items	高度模拟、温度试验、振动、冲击、外部短路、挤压、过度充电、强制放电 Altitude simulation, Thermal test, Vibration, Shock, External short circuit, Crush, Overcharge, Forced discharge.		
测试结论 Conclusion	经测试，该样品符合联合国《试验和标准手册》ST/SG/AC.10/11/Rev.8, 38.3 标准要求。 The sample has passed the test items of UNITED NATIONS "Manual of Tests and Criteria" ST/SG/AC.10/11/Rev.8, 38.3. 签发日期(Issue date): 2025-07-04		
备注 Remark	--		
主检(测试工程师) Tested by: (Test engineer)	李奕霖 King Li (Test Engineer)	李奕霖 King Li	东莞市中认联科检测技术有限公司 Dongguan ZRLK Testing Technology Co., Ltd.
审核(项目工程师) Checker: (Project engineer)	张健斌 Ben zhang (Item Engineer)	张健斌 Ben Zhang	
批准(技术总监) Approver: (Technical director)	马孝琴 Ailis Ma (Approved by)	马孝琴 Ailis Ma	

序号 No.	测试项目名称 Name of test	标准要求或标准条款号 Standard requirement or the clause number of standard	测试结果 Test result	本项结论 Test conclusion	备注 Remarks
1	高度模拟 Altitude simulation	联合国《试验和标准手册》（第8版）38.3 节试验 T.1 UN "Manual of Tests and Criteria" ST/SG/AC.10/11/Rev.8/Subsection 38.3 Test T.1	见附表 1 See Appendix 1	合格 Passed	/
2	温度试验 Thermal test	联合国《试验和标准手册》（第8版）38.3 节试验 T.2 UN "Manual of Tests and Criteria" ST/SG/AC.10/11/Rev.8/Subsection 38.3 Test T.2	见附表 2 See Appendix 2	合格 Passed	/
3	振动 Vibration	联合国《试验和标准手册》（第8版）38.3 节试验 T.3 UN "Manual of Tests and Criteria" ST/SG/AC.10/11/Rev.8/Subsection 38.3 Test T.3	见附表 3 See Appendix 3	合格 Passed	/
4	冲击 Shock	联合国《试验和标准手册》（第8版）38.3 节试验 T.4 UN "Manual of Tests and Criteria" ST/SG/AC.10/11/Rev.8/Subsection 38.3 Test T.4	见附表 4 See Appendix 4	合格 Passed	/
5	外部短路 External short-circuit	联合国《试验和标准手册》（第8版）38.3 节试验 T.5 UN "Manual of Tests and Criteria" ST/SG/AC.10/11/Rev.8/Subsection 38.3 Test T.5	见附表 5 See Appendix 5	合格 Passed	/
6	挤压 Crush	联合国《试验和标准手册》（第8版）38.3 节试验 T.6 UN "Manual of Tests and Criteria" ST/SG/AC.10/11/Rev.8/Subsection 38.3 Test T.6	见附表 6 See Appendix 6	合格 Passed	/
7	过度充电 Overcharge	联合国《试验和标准手册》（第8版）38.3 节试验 T.7 UN "Manual of Tests and Criteria" ST/SG/AC.10/11/Rev.8/Subsection 38.3 Test T.7	见附表 7 See Appendix 7	合格 Passed	/
8	强制放电 Forced discharge	联合国《试验和标准手册》（第8版）38.3 节试验 T.8 UN "Manual of Tests and Criteria" ST/SG/AC.10/11/Rev.8/Subsection 38.3 Test T.8	见附表 8 See Appendix 8	合格 Passed	/
测试环境条件 Test environment condition		环境温度: 20℃ - 25℃; 环境湿度: 45% - 75% Ambient temperature: 20℃ - 25℃, Ambient humidity: 45% - 75%			

Procedure 说明

Tests T.1 to T.5 shall be conducted in sequence on the same cell or battery. Tests T.6 and T.8 shall be conducted using not otherwise tested cells. Test T.7 may be conducted using undamaged batteries previously used in tests T.1 to T.5 for purposes of testing on cycled batteries.

用相同的电芯或电池按照顺序进行试验 T.1 至 T.5。试验 T.6 至 T.8 用没有进行其他试验的电芯。试验 T7 可以使用原先在试验 T1 至 T5 中使用过的未损坏的电池进行，以便测试交替充电放电的电池。

Single cell batteries of B1#~B5#, B11#~B14# are full charged after one cycle;

Single cell batteries of B6#~B10#, B15#~B18# are full charged after twenty-five cycles;

Rechargeable cells of C1#~C5# are 50% charged after one cycle;

Rechargeable cells of C6#~C10# are 50% charged after twenty-five cycles;

Rechargeable cells of C11#~C20# are full discharged after one cycle;

Rechargeable cells of C21#~C30# are full discharged after twenty-five cycles;

Test environment condition: ambient temperature: 15-25℃, ambient humidity: 40-70%

单电芯电池 B1#~B5#, B11#~B14#为 1 次循环满电状态;

单电芯电池 B6#~B10#, B15#~B18#为 25 次循环满电状态;

可充电电芯 C1#~C5#为 1 次循环后 50%充电状态;

可充电电芯 C6#~C10#为 25 次循环后 50%充电状态;

可充电电芯 C11#~C20#为 1 次循环完全放电状态;

可充电电芯 C21#~C30#为 25 次循环完全放电状态;

试验环境条件: 环境温度: 15-25℃, 环境湿度: 40-70%

附表 1

Appendix 1

序号 No.	1	测试项目名称 Name of Test Items	高度模拟 Altitude simulation					
样品编号 Sample No.	测试前 Before		测试后 After		质量损失 Mass loss (%)	剩余电压 Residual OCV (%)	测试结果 Test result	
	电池质量 m ₁ (g)	开路电压 V ₁ (V)	电池质量 m ₂ (g)	开路电压 V ₂ (V)				
B01	134.5315	5.158	134.5180	5.153	0.01	99.9	O	
B02	135.1388	5.159	135.1253	5.154	0.01	99.9	O	
B03	134.8109	5.162	134.7974	5.157	0.01	99.9	O	
B04	134.9322	5.166	134.9187	5.161	0.01	99.9	O	
B05	135.5245	5.160	135.5109	5.155	0.01	99.9	O	
B06	134.3500	5.158	134.3366	5.153	0.01	99.9	O	
B07	134.6834	5.163	134.6699	5.158	0.01	99.9	O	
B08	134.4668	5.162	134.4534	5.157	0.01	99.9	O	
B09	134.7452	5.164	134.7317	5.159	0.01	99.9	O	
B10	134.9914	5.165	134.9779	5.160	0.01	99.9	O	
No. B01-B05: 编号 B01-B05:	At first cycle, in fully charged states 第 1 个充电周期, 完全充电状态							
No. B06-B10: 编号 B06-B10:	After 25 cycles ending in fully charged states 第 25 个充电周期, 完全充电状态							
注: L-泄露; V-排气; D-解体; R-破裂; F-起火; O-无泄露、无排气、无解体、无破裂、无起火。 Note: L-Leakage, V-Venting, D-Disassembly, R-Rupture, F-Fire, O-No leakage, no venting, no disassembly, no rupture & no fire								

附表 2
Appendix 2

Appendix 2

序号 No.	2	测试项目名称 Name of Test Items	温度试验 Thermal test				
样品编号 Sample No.	测试前 Before		测试后 After		质量损失 Mass loss (%)	剩余电压 Residual OCV (%)	测试结果 Test result
	电池质量 m ₁ (g)	开路电压 V ₁ (V)	电池质量 m ₂ (g)	开路电压 V ₂ (V)			
B01	134.5180	5.153	134.4327	5.089	0.06	98.8	O
B02	135.1253	5.154	135.0428	5.088	0.06	98.7	O
B03	134.7974	5.157	134.7090	5.094	0.07	98.8	O
B04	134.9187	5.161	134.8292	5.098	0.07	98.8	O
B05	135.5109	5.155	135.4224	5.092	0.07	98.8	O
B06	134.3366	5.153	134.2482	5.089	0.07	98.8	O
B07	134.6699	5.158	134.5758	5.094	0.07	98.8	O
B08	134.4534	5.157	134.3692	5.091	0.06	98.7	O
B09	134.7317	5.159	134.6376	5.094	0.07	98.7	O
B10	134.9779	5.160	134.8919	5.093	0.06	98.7	O
No. B01-B05: 编号 B01-B05:	At first cycle, in fully charged states 第 1 个充电周期, 完全充电状态						
No. B06-B10: 编号 B06-B10:	After 25 cycles ending in fully charged states 第 25 个充电周期, 完全充电状态						
注: L-泄露; V-排气; D-解体; R-破裂; F-起火; O-无泄露、无排气、无解体、无破裂、无起火。 Note: L-Leakage, V-Venting, D-Disassembly, R-Rupture, F-Fire, O-No leakage, no venting, no disassembly, no rupture & no fire							

附表 3
Appendix 3

Appendix C

序号 No.	3	测试项目名称 Name of Test Items	振动 Vibration				
样品编号 Sample No.	测试前 Before		测试后 After		质量损失 Mass loss (%)	剩余电压 Residual OCV (%)	测试结果 Test result
	电池质量 m ₁ (g)	开路电压 V ₁ (V)	电池质量 m ₂ (g)	开路电压 V ₂ (V)			
B01	134.4327	5.089	134.4012	5.082	0.02	99.9	O
B02	135.0428	5.088	135.0098	5.083	0.02	99.9	O
B03	134.7090	5.094	134.6788	5.088	0.02	99.9	O
B04	134.8292	5.098	134.7915	5.090	0.03	99.8	O
B05	135.4224	5.092	135.3912	5.083	0.02	99.8	O
B06	134.2482	5.089	134.2137	5.079	0.03	99.8	O
B07	134.5758	5.094	134.5409	5.088	0.03	99.9	O
B08	134.3692	5.091	134.3358	5.082	0.03	99.8	O
B09	134.6376	5.094	134.6071	5.086	0.02	99.8	O
B10	134.8919	5.093	134.8593	5.084	0.02	99.8	O
No. B01-B05: 编号 B01-B05:	At first cycle, in fully charged states 第 1 个充电周期, 完全充电状态						
No. B06-B10: 编号 B06-B10:	After 25 cycles ending in fully charged states 第 25 个充电周期, 完全充电状态						
注: L-泄露; V-排气; D-解体; R-破裂; F-起火; O-无泄露、无排气、无解体、无破裂、无起火。 Note: L-Leakage, V-Venting, D-Disassembly, R-Rupture, F-Fire, O-No leakage, no venting, no disassembly, no rupture & no fire							

附表 4
Appendix 4

Appendix 1

序号 No.	4	测试项目名称 Name of Test Items	冲击 Shock				
样品编号 Sample No.	测试前 Before		测试后 After		质量损失 Mass loss (%)	剩余电压 Residual OCV (%)	测试结果 Test result
	电池质量 m ₁ (g)	开路电压 V ₁ (V)	电池质量 m ₂ (g)	开路电压 V ₂ (V)			
B01	134.4012	5.082	134.3878	5.077	0.01	99.9	O
B02	135.0098	5.083	134.9963	5.078	0.01	99.9	O
B03	134.6788	5.088	134.6653	5.083	0.01	99.9	O
B04	134.7915	5.090	134.7780	5.085	0.01	99.9	O
B05	135.3912	5.083	135.3777	5.078	0.01	99.9	O
B06	134.2137	5.079	134.2003	5.074	0.01	99.9	O
B07	134.5409	5.088	134.5274	5.083	0.01	99.9	O
B08	134.3358	5.082	134.3224	5.077	0.01	99.9	O
B09	134.6071	5.086	134.5936	5.081	0.01	99.9	O
B10	134.8593	5.084	134.8458	5.079	0.01	99.9	O
No. B01-B05: 编号 B01-B05:	At first cycle, in fully charged states 第 1 个充电周期, 完全充电状态						
No. B06-B10: 编号 B06-B10:	After 25 cycles ending in fully charged states 第 25 个充电周期, 完全充电状态						
注: L-泄露; V-排气; D-解体; R-破裂; F-起火; O-无泄露、无排气、无解体、无破裂、无起火。 Note: L-Leakage, V-Venting, D-Disassembly, R-Rupture, F-Fire, O-No leakage, no venting, no disassembly, no rupture & no fire							

附表 5

Appendix 5

序号 No.	5	测试项目名称 Name of Test Items	外部短路 External short circuit
样品编号 Sample No.	样品表面最高温度 Max. External Temperature (℃)	测试结果 Test result	备注 Remark
B01	57.6	O	/
B02	57.7	O	/
B03	58.6	O	/
B04	57.6	O	/
B05	58.3	O	/
B06	58.6	O	/
B07	58.7	O	/
B08	58.7	O	/
B09	58.2	O	/
B10	58.1	O	/
No. B01-B05: 编号 B01-B05:	At first cycle, in fully charged states 第 1 个充电周期, 完全充电状态		
No. B06-B10: 编号 B06-B10:	After 25 cycles ending in fully charged states 第 25 个充电周期, 完全充电状态		
注: D-解体; R-破裂; F-起火; O-无解体、无破裂、无起火。 Note: D-Disassembly, R-Rupture, F-Fire, O-No disassembly, no rupture & no fire			

附表 6
Appendix 6

序号 No.	6	测试项目名称 Name of Test Items	挤压 Crush		
样品编号 Sample No.		样品表面最高温度 Max. External Temperature (℃)	测试结果 Test result	备注 Remark	
C01		24.2	O	/	
C02		25.6	O	/	
C03		25.0	O	/	
C04		25.3	O	/	
C05		24.4	O	/	
C06		25.0	O	/	
C07		24.4	O	/	
C08		24.9	O	/	
C09		23.8	O	/	
C10		24.2	O	/	
No. C01-C05: 编号 C01-C05:		At first cycle at 50% of the design rated capacity 第 1 个充放电周期 50%设计额定容量状态			
No. C06-C10: 编号 C06-C10:		After 25 cycle at 50% of the design rated capacity 第 25 个充放电周期 50%设计额定容量状态			
注: D-解体; R-破裂; F-起火; O-无解体、无破裂、无起火。 Note: D-Disassembly, R-Rupture, F-Fire, O-No disassembly, no rupture & no fire					

附表 7
Appendix 7



序号 No.	7	测试项目名称 Name of Test Items	过度充电 Overcharge
样品编号 Sample No		测试结果 Test result	备注 Remark
B11		O	/
B12		O	/
B13		O	/
B14		O	/
B15		O	/
B16		O	/
B17		O	/
B18		O	/
No. B11-B14: 编号 B11-B14:		At first cycle, in fully charged states 第 1 个充电周期, 完全充电状态	
No. B15-B18: 编号 B15-B18:		After 25 cycles ending in fully charged states 第 25 个充电周期, 完全充电状态	
注: D-解体; F-起火; O-无解体、无起火。 Note: D-Disassembly, F-Fire, O-No disassembly & no fire			

附表 8
Appendix 8

序号 No.	8	测试项目名称 Name of Test Items	强制放电 Forced discharge
样品编号 Sample No		测试结果 Test result	备注 Remark
C11		O	/
C12		O	/
C13		O	/
C14		O	/
C15		O	/
C16		O	/
C17		O	/
C18		O	/
C19		O	/
C20		O	/
C21		O	/
C22		O	/
C23		O	/
C24		O	/
C25		O	/
C26		O	/
C27		O	/
C28		O	/
C29		O	/
C30		O	/
No. C11-C20: 编号 C11-C20:		At first cycle in fully discharged states 第 1 个充放电周期，完全放电状态	
No. C21-C30: 编号 C21-C30:		After 25 cycles ending in fully discharged states 第 25 个充放电周期，完全放电状态	
注： D-解体； F-起火； O-无解体、无起火。 Note: D-Disassembly, F-Fire, O-No disassembly & no fire			

样品照片 Sample photo

Model No.: P322.90
Type-C Input: 5V $\overline{=}$ 2.4A Battery Capacity: 5,000mAh/19.25Wh
Wireless Output: 5W Type-C Output: 5V $\overline{=}$ 2.4A



***** The end *****

注意事项 Important Notice

1. 本报告无 ZRLK 盖章无效。
The test report is invalid without the official stamp of ZRLK.
2. 未经本试验室书面同意，不得复制或部分地复制本报告。
Nobody is allowed to photocopy or partly photocopy this report without written permission of ZRLK.
3. 本报告无批准人、审核人及编制人签名无效。
The test report is invalid without the signatures of Approver, Checker and Compiler.
4. 客户必须如实提供样品及资料，并保证申报品名和样品以及运输货物相同，否则本检测单位不承担任何相关责任。
The client should provide samples and relevant data, at the same time, they should guarantee the consistence of the product's name the declared, the samples they provided and the goods to be transported. Otherwise we will not bear any relevant responsibilities.
5. 本报告涂改无效。
The test report is invalid if altered.
6. 对检验报告若有异议，应于收到报告之日起十五天内向检验单位提出。
Objection to the test report must be submitted to ZRLK within 15 days.
7. 本报告仅对送检样品负责。
The test report is valid for the tested samples only.
8. 任何情况下检测单位的赔偿责任都不会超过检测单位就本次检测所收取的检测费用。
ZRLK's liability under no circumstance will exceed the testing fee received from applicant for test conducted hereof this testing report.
9. 本报告中的中文内容仅供参考。
The Chinese contents in this report are only for reference.
10. CNAS 未涉及“☆”的项目。
“☆” item cannot be Accredited by CNAS.